

Technical Data Sheet

Date Prepared: 26JAN16

Date Revised: 24Apr23

Version: 2.0

TDS - SQ Eco Raapzaad Was - korrels - hard - 100% natuurlijk - OBW078

Information

Product Description

This Rapeseed based product is formulated for use in the manufacture of a wide range of candle types including pillar, taper, votive and containers.

Physical Properties

Test	Method	Typical
Viscosity @ 100°C	ASTM D 445	5.5 cSt
Congealing Point	ASTM D938	47°C
Penetration	BS EN 1426	5 dmm
Colour	ASTM D1500	<0.5

Statement

- Formulated from materials whose refining history is fully traceable.
- Has not been tested on animals by ourselves or on our behalf.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users must make their own tests to determine the suitability of these products for their own particular purposes. The company makes no warranty of any kind, expressed or implied, including those of merchantability or fitness for a particular purpose, other than that the material conforms to its applicable current Standard Specifications.